


Glazing design



	First glazing	Second glazing
Gas		Argon 90% 15.00mm
Coating		
First glass	PLANILUX 4.00mm	PLANILUX 5.00mm
Coating	PLANITHERM ULTRA N	
Layer		
Coating		
Second glass		
Coating		

Manufacturing sizes

Nominal thickness : **24.0 mm**
Weight : **22.5 kg/m²**

Luminous factors (EN410-2011)

Transmittance : **79 %**
Outdoor reflectance : **12 %**
Indoor reflectance : **12 %**

Colour rendering :

Ra : **97 Transmittance**
Ra : **96 Outdoor reflectance**

Energy factors (EN410-2011)

Transmittance : **54 %**
Outdoor reflectance : **26 %**
Indoor reflectance : **26 %**
Absorptance A1 : **15 %**
Absorptance A2 : **4 %**

Solar factors (EN410-2011)

g : **0.58**
Shading coefficient : **0.67**

Thermal transmission (EN673-2011) - 0° related to vertical position

Ug : **1.1 W/(m².K)**